



Date of issue : 05/01/2005  
Last. mod. date : 04/07/2008

**Product code****02102 RI-757/60 PP CAVITATED GLOSS WHITE TC AP 901 WG****Description**

Gloss white cavitated polypropylene with an extremely glossy finish, top coated to guarantee a good ink key.

Printing methods: UV letterpress, UV screen, UV flexo, gravure and hot stamping.

Permanent adhesive with high adhesion on apolar substrates such as polyethylene and polypropylene. BGVV and FDA compliance (indirect food contact).

For applications requiring a pearlescent look especially in the cosmetic industry.

**FRONTALE**

Type	Top coated polypropylene
Colour and Finish	White, gloss
Weight	45 g/m <sup>2</sup>
Thickness	60 μ

**ADESIVO**

Reference	AP 901
Type	Acrylic permanent
Min. Appl. Temp.	-5°C
Service Temp.	-40°C/+120°C
Shear	High
Tack FTM9	8 N/inch <sup>2</sup>
FinAdh FTM2	7 N/inch

**SUPPORTO**

Type	1 side siliconised glassine
Colour and Finish	White
Weight	63 g/m <sup>2</sup>
Thickness	56 μ
Transparency	>47 %

**RESISTENZA CHIMICA**

Detergent	No effect (24 Hrs)
Gasoline	No effect (1 Hrs)
SAE20 Motoroil	No effect (24 Hrs)
10% HCl	No effect (10 min)
10% NH4OH	No effect (10 min)

**Storage**

The material must be stored at a temperature of 22°C +/- 2°C and 50% +/- 5% of Relative Humidity. Do not expose to direct sun light.

The area must be dry and clean. Please keep the material in the original packaging when not used in order to protect it from dust and contaminations.

All values presented in this data sheet are typical. Ritrama's data sheets provide only the general characteristics of the Product. It is the responsibility of the Customer and/or End User to determine that the Product is fit for the purpose for which the Customer and/or End User wish to use it. Ritrama can give no guarantee beyond the information given in the data sheet.

Ritrama S.p.A.  
Ritrama S.p.A. Sassoferrato  
Coating Ricofin S.r.l.  
Ritrama S.A.  
Ritrama Ltd.(UK)  
Ritrama Inc. Minneapolis (USA)  
Ritrama Inc. Cleveland (USA)

Tel. +39 02 955 459 1  
Tel. +39 0732 97061  
Tel. +39 02 955 430 1  
Tel. +34 93 729 49 98  
Tel. +44 161 786 1760  
Tel. +1 612 378 2277  
Tel. +1 216 851 2300

info@ritrama.it  
info@ritrama.it  
info@ricofin.it  
ritrama@ritrama.es  
sales@ritrama.co.uk  
info@ritrama.com  
info@ritrama.com